

EAST Search History

Ref #	Hits	Search Query	DBs	Default Operator	Plurals	Time Stamp
L1	3	("3202793" "3341680" "4407441").PN.	US-PGPU B; USPAT	OR	ON	2006/06/09 14:56
L2	15	("1971761" "3100338" "3173202" "3289293" "3368272" "3872577" "4027367").PN. OR ("4407441").URPN.	US-PGPU B; USPAT; USOCR	OR	ON	2006/06/09 15:07
L9	3	("3341680").URPN.	USPAT	OR	ON	2006/06/09 15:12
L31	378	228/165.ccls.	US-PGPU B; USPAT; EPO; JPO; DERWENT	OR	ON	2006/06/09 15:58
L32	379	228/262.5.ccls.	US-PGPU B; USPAT; EPO; JPO; DERWENT	OR	ON	2006/06/09 17:18
L33	526	228/262.51.ccls.	US-PGPU B; USPAT; EPO; JPO; DERWENT	OR	ON	2006/06/09 15:16
L34	211	228/176.ccls.	US-PGPU B; USPAT; EPO; JPO; DERWENT	OR	ON	2006/06/09 17:18

EAST Search History

L35	469	228/208.ccls.	US-PGPU B; USPAT; EPO; JPO; DERWEN T	OR	ON	2006/06/09 17:19
L45	11559	(braz\$3 or weld\$3 or solder\$3) and (Al or aluminum or aluminium or iron or steel) and (copper or Cu) same (coat\$3 or layer or plat\$3) and filler	US-PGPU B; USPAT; EPO; JPO; DERWEN T	OR	ON	2006/06/09 18:47
L51	15	(braz\$3 or weld\$3 or solder\$3) with (Al or aluminum or aluminium or Ti or titanium) with (iron or steel) with zinc with (coat\$3 or layer or plat\$3) with filler	US-PGPU B; USPAT; EPO; JPO; DERWEN T	OR	ON	2006/06/09 19:03
L52	46	37 and (braz\$3 or weld\$3 or solder\$3) and (Al or aluminum or aluminium or Ti or titanium) and (iron or steel) and zinc and (coat\$3 or layer or plat\$3) and filler	US-PGPU B; USPAT; EPO; JPO; DERWEN T	OR	ON	2006/06/09 19:13
L53	58	(braz\$3 or weld\$3 or solder\$3) with corrosion with lacquer	US-PGPU B; USPAT; EPO; JPO; DERWEN T	OR	ON	2006/06/09 19:20
L54	8	("4421828" "4501802" "4579786" "4601957"). PN. OR ("4816348"). URPN.	US-PGPU B; USPAT; USOCR	OR	ON	2006/06/09 19:15
L55	6	54 and lacquer	US-PGPU B; USPAT; EPO; JPO; DERWEN T	OR	ON	2006/06/09 19:16

EAST Search History

L56	102	(braz\$3 or weld\$3 or solder\$3) with joint with chamfer	US-PGPU B; USPAT; EPO; JPO; DERWEN T	OR	ON	2006/06/09 19:24
L57	699	(braz\$3 or weld\$3 or solder\$3) with joint with deform\$3	US-PGPU B; USPAT; EPO; JPO; DERWEN T	OR	ON	2006/06/09 19:25
L58	494	(braz\$3 or weld\$3 or solder\$3) near5 joint with deform\$3	US-PGPU B; USPAT; EPO; JPO; DERWEN T	OR	ON	2006/06/09 19:25
L59	6	58 and (Al or aluminium or aluminum or steel or iron) same zinc same (coat\$3 or layer or deposit\$3)	US-PGPU B; USPAT; EPO; JPO; DERWEN T	OR	ON	2006/06/09 19:27